Remineralizing Effect of Xilitol, Juniperus Communis and Camellia Sinensis Added to a Toothpaste: An *In Vitro* Study

Efecto remineralizante del Xilitol, Juniperus Communis y Camellia Sinensis adicionados en pastas dentales: Estudio *in vitro*

> Sandra I. Jiménez-Gayosso DDS^{1,2}; Edith Lara-Carrillo DDS, MSc, PhD¹; Rogelio J. Scougall-Vilchis DDS, MSc, PhD¹; Raúl A. Morales-Luckie BS Chem, PhD³; Carlo E. Medina Solís DDS, MSc^{1,2}; Ulises Velázquez-Enríquez DDS, MSc, PhD¹; Gerardo Maupomé DDS, MSc, PhD^{4,5}; Brenda-Herrera-Serna DDS, MSc^{1,6}

1. Advanced Studies and Research Centre in Dentistry "Dr. Keisaburo Miyata" of Faculty of Dentistry at Autonomous University State of Mexico, Toluca, Mexico.

 Academic Area of Dentistry of Health Sciences Institute at Autonomous University of Hidalgo State, Pachuca, Mexico.
Sustainable Chemistry UAEMex-UNAM Research Center of Faculty of Chemistry at Autonomous University State of Mexico, Toluca, Mexico.

4. Richard M. Fairbanks School of Public Health, Indiana University/Purdue University in Indianapolis. Indianapolis, USA.
5. Indiana University Network Science Institute. Bloomington, USA.

6. Autonomous University of Manizales, Colombia.

Correspondence to: Dra. Edith Lara-Carrillo - laracaedith@hotmail.com

Received: 1-VIII-2018

Accepted: 11-IX-2018

Published Online First: 18-IX-2018

DOI:

ABSTRACT

The aim of this study was to explore the remineralizing effect of toothpastes based on Xilitol, Camellia Sinensis and Juniperus Communis. An *in vitro* experimental study was carried out in an 18 human premolars sample, which were treated with one of the 3 evaluated toothpastes and a control fluoride one. The atomic percentages of Ca and P were evaluated by Energy Dispersive X-ray Spectroscopy (EDS). In addition, the enamel surface of treated teeth was visualized by Scanning Electron Microscopy (SEM). The evaluations were carried out in three stages: pre-treatment, after an artificial demineralization process and after the treatment with the toothpastes. In the statistical analysis, the one-way ANOVA and Pearson correlation tests were used. Xilitol and Juniperus Communis showed the greatest gain of P ions compared to the control group (p<0.01). As for Ca, the group treated with xylitol-based toothpaste showed more ion gain compared with the control group (p<0.01). In the Pearson correlation test between Ca and P, statistically significant correlations were observed in all groups (p<0.01), ranging between r=0.7413 (Xylitol Group) and r=0.9510 (Control Group). We concluded that Xylitol paste showed the highest remineralizing property, both in the EDS analysis and in the SEM images.

KEYWORDS

Remineralization; Xylitol; Juniperus Communis; Camellia Sinensis; Toothpaste; In Vitro Techniques.

JIMÉNEZ S., LARA E., SCOUGALL R., MORALES R., MEDINA C., VELÁZQUEZ U., MAUPOMÉ G., HERRERA B., 2018: Remineralizing Effect of Xilitol, Juniperus Communis and Camellia Sinensis Added to a Toothpaste: An *In Vitro* Study.-ODOVTOS-Int. J. Dental Sc., .

RESUMEN

El objetivo de este studio fue explorer el efecto remineralizante de las cremas dentales compuestas de Xilitol, Camelia Sinensis y Juniperus Communis. Se llevó a cabo un estudio experimental *in vitro* en una muestra de 18 premolares humanos, los cuales fueron tratados con una de las tres pastas dentales evaluadas y una fluorada. Los porcentajes atomicos de Ca y P fueron evaluados por Espectroscopia de rayos X de energía dispersive (EDS). Además, la superficie del esmalte de los dientes tratados fue examinada por Microscopia Electronica de Barrido (SEM). Las evaluaciones fueron llevadas a cabo en tres etapas: pre-tratamiento, despues de un proceso artificial de desmineralizacion y después del tratamiento con las pastas dentales. Se usaron ANOVA de una via y correlacion de Pearson para el analisis estadístico. Xilitol y Juniperus Communis mostraron la mayor ganancia de iones P comparados con el grupo control (p<0.01), con rangos entre r=0.7413 (Grupo con Xylitol) and r=0.9510 (Group Control). Se concluyó que la pasta con Xilitol mostró las mayores propiedades remineralizantes, tanto en el analisis EDS y las imágenes SEM.

PALABRAS CLAVE

Remineralizacion; Xylitol; Juniperus communis; Camellia sinensis; Pasta dental; Técnicas in vitro.

INTRODUCTION

The balance of demineralization and remineralization in dental caries is fundamental to understand the presence and progress of initial or subclinical lesions (1-3). These cycles are a complex series of events on the tooth surface, which take place in ecological changes within the dental biofilm (4,5). At the beginning they are observed clinically as a small demineralized area. Remineralization is a net gain of ions towards the dental tissues, which replaces the loss due to the demineralization process. This occurs through a physical-chemical process that includes the supersaturation of ions in the solution in relation to enamel, the formation of nucleus and crystals (6,7). Since the control of dental caries remains a challenge (8) as one of the main public health problems in the world, its negative impacts should not be underestimated. Among other effects, dental pain, tooth loss, effects on general wellbeing and quality of life must be mentioned (9,10). It is important to look for effective treatments to prevent the disease in its incipient stages (1-3). The importance of fluoride is indisputable as a viable and economical method; most likely, it will continue to lead the prevention of dental caries. However, there are compounds that serve as adjuvants in the remineralization process (11). Currently there is a growing interest in options that do not contain fluoride. These compounds are biologically active, mainly derived from natural products such as tea (eg, Camellia Sinensis or green tea), coffee, grapes, propolis, as well as some Asian herbs and mushrooms (12), synthetics products such as amorphous calcium phosphate, casein and xylitol (13-15). Xylitol [(CHOH) 3(CH2OH) 2] is a non-acidic sweetener; it is associated with Ca in aqueous solution to inhibit the dissolution of enamel's calcium or phosphate ions, thus acting as a calcium transporter required for enamel remineralization (16).

The objective of this article was to evaluate the remineralizing effect of toothpastes based on Xylitol, and of two biologically active natural botanical agents, Camellia sinensis and Juniperus communis. This exploration of its remineralizing potential was compared against a fluoridated toothpaste.

MATERIALS AND METHODS

An experimental in vitro study was carried out. The protocol was reviewed and approved by the Research and Ethics Committee of the Autonomous University State of Mexico.

We included 18 human premolars extracted for orthodontic reasons. All the patients signed an informed consent.

Bicuspids had no restorations, fractures or decay on the vestibular face. The teeth were stored in 0.2% thymol after extraction. Teeth were randomly assigned to one of six groups. Control group, which was not exposed to any procedure; Demineralization only group, exposed to an artificial demineralization process; Xilitol group, exposed to 100% Natural Dentiste toothpaste (Bangkok, Thailand); Camelia sinensis group, exposed to Fluocaril toothpaste (Bangkok, Thailand); Juniperus communis group, exposed to Splat Special Blackwood toothpaste (Moscow, Russia); and Toothpaste Control Group, exposed to Colgate Triple Action toothpaste (San Jose Iturbide, Guanajuato, Mexico).

ALL THE TEETH WERE SUBJECTED TO THE FOLLOWING PROCESSES FOR FURTHER ANALYSIS

ARTIFICIAL DEMINERALIZATION PROCESS

An artificial demineralization process was performed, for which the specimens were immersed in a demineralizing solution (2.2 Mm CaCl2, 2.2 Mm NaH2PO4, 0.05 Mm CH3COOH and 1M KOH) adjusting the pH to 4.4 during 96 hours at 37 ° C in an incubator (17). CYCLIC PH MODEL

The specimens were exposed to a cyclic pH model for 15 days at 37°C in order to simulate the conditions of the oral environment.

Each specimen was immersed in a demineralizing solution (2.2Mm CaCl2, 2.2Mm NaH2PO4, 0.05 Mm CH3COOH, 1M KOH, pH 4.4, 10 mL/specimen) twice a day for 3 hours and for 2 hours in the remineralizing solution (1.5Mm CaCl2, 0.9Mm NaH2PO4, 0.15Mm KCl, pH 7.0, 10mL / specimen) between the demineralization cycles.

The specimens treated with the toothpastes were embedded in suspension of toothpaste according to their group (5 mL per specimen) for 60s before the onset of the first demineralization cycle and before and after the second demineralization cycle. Then, they were stored in remineralizing solution in an incubator at 37°C for 16 hours to complete 24 hours of a cycle (17).

TEETH PREPARATION FOR ANALYSIS BY SEM AND EDS

We obtained 3x3 mm blocks of enamel from the vestibular surface of the teeth. They were cut with a carbide disc, then we cleaned of specimens for 5 minutes in separate containers, filled with tri-distilled water in an ultrasonic bath (Quantrex Q140, L & R Ultrasonics, NJ, USA). Next, the blocks were fixed to an aluminum specimen holder with carbon adhesive tape (SPI Supplies, USA).

The atomic percentages of Ca and P were evaluated, which were analyzed with EDS. In addition, the enamel surface was visualized by SEM.

The SEM analysis was performed using a scanning electron microscope (JEOL, JSM-6510LV, Japan) in the low vacuum mode at 10 Pa of pressure

in the chamber, with an electron acceleration voltage of 15 kV and detecting backscattered electrons.

The morphology of the enamel surface was observed at a magnification of 500x at a working distance of 50 mm. We determined the atomic percentages (% at) of Ca and P using an X-ray detector system (Oxford Instruments, 7582, United Kingdom) coupled to the scanning electron microscope.

STATISTICAL ANALYSIS

Data were analyzed using the statistical package SPSS 23.0 (SPSS Inc., Chicago, USA). The one-way ANOVA test was performed with Bonferroni's correction for multiple comparisons of atomic percentages of Ca and P; the value of p was adjusted to 0.001667. We also used the Pearson Correlation test between Ca and P, with a significance of $p \le 0.05$.

RESULTS

QUANTITATIVE EVALUATION OF CHEMICAL COMPOSITION WITH EDS

The chemical composition of the enamel surface was determined before treatment, after a demineralization process and after the treatment with each of the remineralizing toothpastes, which were presented in at%.

Table 1 shows the results of the atomic percentage analysis of the Ca and P elements of each study group. In the Pearson correlation

test between Ca and P, statistically significant correlations were observed in all groups (p < 0.01), ranging from r=0.7413 (Xylitol Group) to r= 0.9510 (Control Group).

When performing the one-way ANOVA test for the comparison of P, statistically significant differences were found between the Control Toothpaste Group vs the Xylitol Group (p<0.001), the Control Toothpaste Group vs the Camelia Sinensis Group (p=0.003) and between the Control Toothpaste Group vs Juniperus Communis Group (p<0.001). With respect to Ca, statistically significant differences were obtained between the Xylitol Group vs. the Demineralization Group (p=0.001) and between the Control Toothpaste Group vs the Xylitol Group (p<0.001) (Table 2 and 3).

QUALITATIVE ANALYSIS WITH SEM OF THE SPECIMENS' SURFACES

In Fig. 1 we observe the microphotographs representative of the SEM enamel surfaces analysis for the groups. In the pretreatment analysis of the enamel surface morphology, shown in Fig.1a), we observe the prisms exposed in a "key hole" shape, as well as in a circular form. On the enamel surface after artificial demineralization we can observe a smooth appearance without perikymata pattern, with irregular fissures, as well as small defects in its periphery and presence of numerous irregular holes (Fig.1b). In the enamel surfaces treated with the toothpastes studied, smooth surfaces with various porosities and grooves were found in the goups treated with Camellia Sinensis and Juniperus Communis toothpastes (Fig.1c-f).

Chemical element at%	Control Group	Demineralization Group	Xylitol Group	Camelia sinensis Group	Juniperus communis Group	Control Toothpaste Group	F	p value*
Са	16.96±3.56	15.22±1.57	21.01±3.05	17.19±4.48	17.77±1.67	14.66±4.70	6.8	0.000
Р	11.38±2.33	11.15±1.10	12.93±1.56	12.26±2.02	13.03±1.00	9.31±2.51		
Correlation†	r= 0.9510 p<0.0010	r= 0.9161 p<0.0010	r=0.7413 p=0.0058	r=0.9371 p<0.0010	r=0.9161 p<0.0010	0.7626 p<0.0012		

Table [*]	1. Analysi	s of the	Ca and P	element	atomic	percentage.
--------------------	------------	----------	----------	---------	--------	-------------

* Analysis of variance (ANOVA) † Pearson correlation of Ca y P

Table 2. Multiple comparisons of Bonferroni for P.

	Control Group	Demineralization Group	Xylitol Group	Camelia sinensis Group	Juniperus communis Group
Demineralization Group	-0.2325 1.000				
Xylitol Group	1.5525 0.662	1.785 0.319			
Camelia sinensis Group	.8775 1.000	1.11 1.000	-0.675 1.000		
Juniperus communis Group	1.65 0.491	1.8825 0.231	0.0975 1.000	0.7725 1.000	
Control Toothpaste Group	-2.0725 0.119	-1.84 0.266	-3.625 0.000	-2.95 0.003	-3.7225 0.000

*The p value was adjusted to a significance of 0.001667.

Table 3. Multiple Bonferroni comparisons for Ca.

	Control Group	Demineralization Group	Xylitol Group	Camelia sinensis Group	Juniperus communis Group
Demineralization Group	-1.74 1.000				
Xylitol Group	4.04583 0.074	5.78583 0.001			
Camelia sinensis Group	.224167 1.000	1.96417 1.000	-3.82167 0.116		
Juniperus communis Group	.811666 1.000	2.55167 1.000	-3.23417 0.347	.5875 1.000	
Control Toothpaste Group	-2.29833 1.000	558333 1.000	-6.34417 0.000	-2.5225 1.000	-3.11 0.431

*The p value was adjusted to a significance of 0.001667.



Figure 1. a) Pretreatment enamel surface morphology, b) Enamel surface after an artificial demineralization process, c) Enamel surface after treatment with xylitol toothpaste, d) Enamel surface after Camellia sinensis.

DISCUSSION

In the present study, the remineralizing effect of Xylitol, Camellia sinensis and Juniperus communis added to dentifrices was evaluated, using a fluoride toothpaste as a control. We studied the morphological and chemical changes of human premolars enamel surface after their treatment with the toothpastes previously mentioned. It was found that specimens treated with the Juniperus communis toothpaste had a higher atomic percentage of P; however, it cannot be definitively concluded if this result is due to the active component of Juniperus communis, since pyrophosphates are found within the ingredients of this toothpaste. On the other hand, when analyzing the atomic percentages of Ca, statistically significant differences were observed between the group treated with the Xylitol toothpaste and the control group. This ion gain benefits the remineralization process by the net addition into the enamel structure, which replaces what was previously lost by demineralization. It should be mentioned that this occurs through a physical-chemical process that includes the ions supersaturation of the solution respecting to enamel, the formation of nucleus and crystal growth (18,19).

It is well known that Xylitol in high concentrations has the ability to form compounds with calcium ions and penetrate the demineralized enamel, where it can contribute to transporting dissolved ions by decreasing the calcium and phosphate diffusion coefficient (15,20). Studies have shown greater remineralizing effect in both varnishes (15) and in toothpastes (21) when xylitol is added to fluoride. In our study we found a positive correlation between the presence of calcium and phosphorus; however, this was the weakest correlation, even compared with the control toothpaste group. In vivo studies have shown that the remineralization process can be accelerated because xylitol reduces the acidity of the bacterial biofilm, allowing fluoride to act under more favorable conditions (22).

Recent studies have shown the remineralizing effect of Camellia sinensis (23,24) Likewise, it has been shown that its addition to carbonated drinks reduces the demineralization they cause (25). In this study we found that the addition of this compound to toothpastes helps to increase calcium and phosphate ions, obtaining a strong correlation. These results are not definitive: in a dynamic environment such as the mouth, antibacterial effects should be evaluated (26). It should be determined whether remineralization is influenced by the variable fluoride levels in the Camellia sinensis leaves (27).

Reviewing the literature, no evidence was found of the Juniperus communis remineralizing effect (28) However, its antioxidant effect has been proven, which is directly related to its application to prevent oxidative damage to biological systems by reactive forms of oxygen H2, O2, O2- and OH) that are produced during cellular metabolism in organisms (29,30). It is worth mentioning that, in the present study, an almost perfect correlation was found between the amount of calcium and phosphate ions when applying the Juniperus communis toothpaste (28). For these reasons it is advisable to perform in vivo studies to evaluate these effects - both the effects of the different types of Juniperus by themselves, and in conjunction with pyrophosphates in the toothpaste.

Although the use of fluorides is essential in the prevention of dental caries, it is important to explore the value of available alternatives. The present research aims to expand the knowledge about remineralizing substances that are not based on fluoride. These have become attractive for patients interested in using products that are perceived to be biologically natural alternatives, or with fluorides excluded in their formulation. The cultural tendency to exclude fluorides from watermanifested in multiple votes in developed countries in which local populations reject the addition of fluorides to drinking water-makes it necessary to evaluate the different options available in the market for prevention of dental caries.

This study has the limitation that it was undertaken in a small sample. Despite its exploratory nature, our results confirm some past literature reports, and provide new evidence. Xylitol toothpaste showed the highest remineralizing property, both in the EDS analysis and in the SEM images. Although the Camelia sinensis toothpaste showed positive results by EDS, the SEM images showed a smooth surface, similar to the demineralized surface. The Juniperus communis toothpaste was associated with a high percentage of phosphate; this may be due to the fact that its composition includes pyrophosphates, which can form synthetic phosphates.

REFERENCES

- Abdulraheam R. H., Garib B. T. Effect of different tea in remineralization of artificiallyinduced initial enamel caries of human teeth (Study in vitro). J Dent Sci (Tikrit) 2011; 1:19-24.
- Ando M., Ferreira-Zandoná A. G., Eckert G. J., Zero D. T., Stookey G. K. Pilot clinical study to assess caries lesion activity using quantitative light-induced fluorescence during dehydration. Journal of Biomedical Optics 2017; 22: 03: 50-55.
- Anita P., Sivasamy S., Madam-Kumar P. D., Balan I. N., Ethiraj S. In vitro antibacterial activity of Camellia sinensis extract against cariogenic microorganisms. J Basic Clin Pharm 2014; 6: 35-39.
- Arends J., Christoffersen J., Schuthof J., and Smits M. T. Influence of xylitol on demineralization of enamel. Caries Res 1984; 18: 296-301.
- Azzimonti B., Cochis A., El Beyrouthy M., Iriti M, Uberti F, Sorrentino R, et al. Essential oil from berries of lebanese Juniperus excelsa M. Bieb displays similar antibacterial activity to chlorhexidine but higher cytocompatibility with human oral primary cells. Molecules 2015; 20: 9344-9357.
- 6. Barbosa C. S., Kato M. T., Buzalaf M. A. R. Effect of supplementation of soft drinks with green tea extract on their erosive potential against dentine. Aust Dent J 2011; 56: 317-321.
- Cardoso C. A., Cassiano L. P., Costa E. N., Souza-E-Silva C. M., Magalhães AC, Grizzo LT, et al. Effect of xylitol varnishes on remineralization of artificial enamel caries lesions in situ. J Dent 2016b; 50: 74-78.
- Cardoso J. G., Iorio N. L., Rodrigues L. F., Couri M. L., Farah A., Maia L. C., et al. Influence of a Brazilian wild green propolis on the enamel mineral loss and Streptococcus mutans' count in dental biofilm. Arch Oral Biol 2016a; 65: 77-81.

- Castellanos J. E., Marín L. M., Úsuga M. V., Castiblanco G. A., Martignon S. La remineralización del esmalte bajo el entendimiento actual de la caries dental. Univ Odontol 2013; 32: 49-59.
- 10. Cheng L., Li J., He L., Zhou X. Natural products and caries prevention. Caries Res 2015; 49: 38-45.
- Cochrane N. J., Cai F., Huq N. L., Burrow M. F., Reynolds E. C. New approaches to enhanced remineralization of tooth enamel. J Dent Res 2010; 89: 1187-1197.
- Donahue G. J., Waddell N., Plough A. L., del Aguila M. A., Garland T. E. The ABCDs of treating the most prevalent childhood disease. Am J Public Health 2005; 95: 1322-1324.
- Ekambaram M., Itthagarun A., King N. M. Comparison of the remineralizing potential of child formula dentifrices. Int J Paediatr Dent 2011; 21: 132-140.
- Featherstone J. D. The science and practice of caries prevention. J Am Dent Assoc 2000; 131: 887-899.
- 15. Grewal N., Gumber S., Kaur N. Comparative evaluation of enamel remineralization potential of processed cheese, calcium phosphate-based syntetic agent, and a fluoride-containing toothpaste: An in situ study. J Indian Soc Pedod Prev Dent 2017; 35: 19-27.
- Hariri I., Sadr A., Nakashima S., Shimada Y., Tagami J., Sumi Y. Estimation of the enamel and dentin mineral content from the refractive index. Caries Res 2013; 47: 18-26.
- Höferl M., Stoilova I., Schmidt E., Wanner J., Jirovetz L., Trifinova D., et al. Chemical composition and antioxidant properties of Juniper Berry (Juniperus communis L.) essential oil. Action of the essential oil on the antioxidant protection of Saccharomyces cerevisiae model organism. Antioxidants (Basel) 2014; 3: 81-98.
- Innes N. P., Frencken J. E., Bjorndal L., Maltz M., Manton D. J., Ricketts D., et al. Managing

carious lesions: Consensus recommendations on terminology. Adv Dent Res 2016; 28: 49-57.

- Khurshid Z., Zafar M. S., Zohaib S., Najeeb S., Naseem M. Green tea (Camellia sinensis): Chemistry and oral health. Open Dent J 2016; 10: 166-173.
- Longbottom C. L., Huysmans M. C., Pitts N. B., Fontana, M. Glossary of key terms. Monogr Oral Sci. 2009; 21: 209-216.
- Mäkinen K. K., Isotupa P. K., Kivilompolo T., Makinen L. P., Tiovanen J., Soderling E. Comparison of erythritol and xylitol saliva stimulants in the control of dental plaque and mutans streptococci. Caries Res 2001; 35: 129-135.
- 22. Malekafzali B., Ekrami M., Mirfasihi A., Abdolazimi Z. Remineralizing Effect of Child Formula Dentifrices on Artificial Enamel Caries Using a pH Cycling Model. J Dent (Tehran) 2015; 12 (1): 11-17.
- 23. Martorell P., Forment J. V., de Llanos R., Montón F., Llopis S., González N., Genovés S., Cienfuegos E., Monzó H., Ramón D. Uso de Saccharomyces cerevisiae y Caenorhabditis elegans como modelo organismos para estudiar el efecto de los polifenoles del cacao en la resistencia al estrés oxidativo. J. Agric. Comida Chem. 2011; 59: 2077-2085.
- 24. Masood M., Yusof N., Hassan M. I., Jaafar N. Longitudinal study of dental caries increment in Malaysian school children: a 5-year cohort

study. Asia Pac J Public Health 2014; 26: 260-267.

- Miake Y., Saeki Y., Takahashi M., Yanagisawa T. Remineralization effects of xylitol on demineralized enamel. J Electron Microsc 2003; 52 (5): 471-476.
- 26. Mirkarimi M., Toomarian L. Effect of green tea extract on the treatment of dentin erosion: an in vitro study. J Dent (Tehran) 2012; 9: 224-228.
- Peres M. A., Barros A. J., Peres K. G., Araujo C. L., Menezes A. M. Life course dental caries determinants and predictors in children aged 12 years: a population-based birth cohort. Community Dent Oral Epidemiol 2009; 37: 123-133.
- Rochel I. D., Souza J. G., Silva T. C., Pereira A. F. F., Rios D., Buzalaf M. A. R., et al. Effect of experimental xilitol and fluoride containing dentifrices on enamel erosion with or without abrasion in vitro. J Oral Sci 2011; 53: 163-168.
- 29. Spratt D. A., Daglia M., Papetti A., Stauder M., O'Donell D., Ciric L., et al. Evaluation of plant and fungal extracts for their potential antigingivitis and anticaries activity. J Biomed Biotechnol 2012; 2012: About 12 pages.
- Ten Cate J. M., Arends J. Remineralization of artificial enamel lesions in vitro: III. A study of the deposition mechanism. Caries Res 1980; 14 (6): 351-358.



Attribution (BY-NC) - (BY) You must give appropriate credit, provide a link to the license, and indicate if changes were made. You may do so in any reasonable manner, but not in any way that suggest the licensor endorses you or your use. (NC) You may not use the material for commercial purposes.